- SNOWA R310 is an EPS class, in accordance with REACH regulative, ensuring rapid molding with its short cycle time, which can be used in production of EPS foam typically in density ranges between 14-25 kg/m3 suitable for high quality block molding and shape molding.

- SNOWA R310 is used for cases and packaging production suitable for food contact, insulation applications which is not requiring fire classification.

- Lower densities can be achieved by multiple expansions.

Bead size - Diameter	0.7 - 1 mm
Blowing agent - Pentane	5.6 - 7 %
Residual Styrene Monomer	Less than 1000 ppm
Moisture content	Less than 0.4 %
CFC content: Nil	Nil
Density	13 - 25 Kg/m3