GPPS 1028

پتروپاک مشرق زمین
PETRO PAAK MASHREGH ZAMIN

Typical applications:

It is recommended for XPS sheets and plates, and extruded embossed sheets, and its suitable for food applications.

Processing:

-Extrusion
-Molding

TECHNICAL PROPERTIES

Physical Properties	Unit	Value	Standard Method
Density	g/cc	1.04	D 792
Melt Flow Index (200 °C/ 5kg)	g/10min	2.4	D 1238
Linear mold shrinkage	%	0.4-0.7	D 955
Styrene residual monomer	ppm	<500	CLGLABPSG004

Mechanical Properties	Unit	Value	Standard Method
Tensile Strength at Yield	MPa	51	D 638
Tensile Elongation at Break	%	3	D 638
Tensile Modulus	MPa	2600	D 638
Flexural Properties			
Strength	MPa	92	D 790
Modulus	MPa	3200	D 790
Izod Impact Resistance (23°C)	KJ/m²	1.5	D 256
Hardness, Rockwell	M scale	78	D 785

Thermal Properties	Unit	Value	Standard Method
Vicat Softening Temperature (50°C/h,1 kg)	°C	102	D 1525
Heat Deflection Temperature(Method B, 0.45 MPa)	°C	94	D 648

Optical Properties	Unit	Value	Standard Method
HAZE	%	2	D 1003

Flammability	Unit	Value	Standard Method
Flammability		HB	UL 94

Product description:

General purpose polystyrene GPPS 1028 is manufactured by continuous mass polymerization of styrene monomer. It has very high molecular weight, high heat grade, high melt strength, good clarity and mechanical strength.

Packaging:

GPPS 1028 is supplied in the form of cylindrical of approximately 2.5×2.5 mm. The product can be supplied in either 25 kg bags.

پتروپاک
PETROPAAK
www.petropaak.com
Email : Sales@petropaak.ir
Tel : +98 21 47199
Unit 404, 4th Floor, No. 1, Aysan Complex, 2 Tehran/Iran

پترو پاک مشرق زمین
PETRO PAAK MASHREGH ZAMIN

Regulatory information:

It is responsibility of the manufacturers of food contact articles and industrial food packers to make sure the article in their actual use are in compliance with the imposed migration requirements.

All mechanical properties measured under standard conditions 50% RH and 23C.

Edit date: 11/05/2024



پترو پاک
PETROPAAK
www.petropaak.com
Email : Sales@petropaak.ir
Tel : +98 21 47199
Unit 404, 4th Floor, No. 1, Aysan Complex, 2
Tehran/Iran