This grade is high strength & good moldability polystyrene .

Main Applications :

Extrusion and thick-walled injection molding Or PS Foam, Office Stationary, Thick walled food containers, etc.

TECHNICAL SPECIFICATION

PROPERTIES	UNIT	VALUE	STANDARD
Tensile Strength (Yield)	(kg/cm^2)	500	D-638
Tensile Modulus of Elasticity	(kg/cm^2)	2.6×10^4	D-638
Izod Impact Strength (notched,t=6.4 mm)	(kg-cm/cm)	2.2	D-256
Vicat Softening Point (50°C/hr ,1000 g)	(°C)	98	D-1525
Melt Index (200°C , 5000 g)	(g/10 min)	6	D-1238

***All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. Which is included MFI and Vicat .**

**** TJPAPC Guaranteed items are MFI and Vicat .**