Producer	Characteristic Properties	Applications
BAKHTAR	Low distortion tendency - High hardness and rigidity - Good ESCR	Thick-Walled, Transport Containers e.g. refuse bins & fish crates - Pallet, Boxes, Screw caps - Cable clips.

Typical Properties

Resin Properties	Unit	Typical Value	Test Method
MFI @ 190°C, 2.16 kg	gr/10min	3.2-4.8	ASTM D1238-10
MFI @ 190°C, 21.6 kg	gr/10min	109	ASTM D1238-10
Density	gr/ml	0.950-0.958	ASTM D1505-10
VOLATILES	%WT	MAX 0.05	IN HOUSE
Standard Yellow Index	-	Min 2.5	DIN 6167