Producer	Characteristic Properties	Applications	Additive
JAM	High stiffness with good physical properties.	Injection molding grade Crates	60505:Thermal Antioxidant Catalyst neutralizer 60505UV:Catalyst eutralizer

Typical Properties

Resin Properties	Unit	Typical Value	Test Method
Melt Index (190°C/ 2.16Kg)	g/10 min	5.5	D1238
Density	g/ml	0.958	D1505
Flexural modulus	MPa	1460	D790
Notched Izod impact at 23°C	J/m	30	D256/A
Vicat softening point	°C	125	D1525