2 Applications:

Pipe Extrusion PE100 Class

- Pressure pipe.
- Drinking water and gas pipes.
- Discharge pipes.
- Sewer pipes and their fittings.
- For injection moulded and other fit tings.
- Sheets



HD 10

No.	Property	Unit	Test Method	Value
1	MFR(190 °C/5Kg)	g/10min	ISO 1133	0.45 ± 0.05
2	MFR(190 °C/21.6Kg)	g/10min	ISO 1133	12.0 ±3.0
3	FRR21.6/5	----	----	28±4
4	Density	g/cm³	ISO 1183	0.945 ± 0.002
5	Notched Impact Strength	mj/mm²	ISO179/1eA	> 12
6	Pipe Evaluation Hydrostatic Strength (80oc,4N/mm2)	Hours	(DIN 8074 & DIN 8075 & ISO 1167)	1000 min.