Producer	Additive	Applications
BAKHTAR	Antioxidants: Irganox1010& Irgafos168 Neutralizer: Calcium Stearate Slip Agent & Antiblocking Agent	Light & Medium Duty film

Typical Properties

Resin Properties	Unit	Typical Value	Test Method
Melt Flow Rate (MFR) 190 °C/2.16 kg	g/10min	2±0.2	ASTM D-1238
FRR (MFR 21.6/2.16)	-	24-26	ASTM D-1238
Density	gr/cm^3	0.922±0.002	ASTM D1505
Contamination	Number	<30	MTM 17064 E
Yellowness Index	-	<0.5	ASTM E313
Dart Impact	gr	123	ASTM D-1709/a
Haze	%	17	ASTM D-1003
Gloss (60°)	-	60	ASTM D-2457
Tensile Modulus	Mpa	-	ASTM D-882
Tensile Strength @Break (TD/MD)	Mpa	31/33	ASTM D-882
Elongation @Break (TD/MD)	%	1070/985	ASTM D-882
Elmendorf Tear (TD/MD)	gf/µm	300/225	ASTM D-1922